

FORM PTO-1390
(REV. 11-2000)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

PHILLIPS-1

U.S. APPLICATION NO. (If known, see 37 CFR 1.5)

09/936599

INTERNATIONAL APPLICATION NO.

PCT/AU00/00197

INTERNATIONAL FILING DATE

17 MARCH 2000

PRIORITY DATE CLAIMED

17 MARCH 1999

TITLE OF INVENTION

RADIATION CURABLE RESIN COMPOSITION

APPLICANT(S) FOR DO/EO/US

BOLTON, et al.

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☐ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below.
4. ☒ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☒ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☐ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☐ is attached hereto.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☐ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11 to 20 below concern document(s) or information included:

11. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A **FIRST** preliminary amendment.
14. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
15. ☐ A substitute specification.
16. ☐ A change of power of attorney and/or address letter.
17. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
18. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
19. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
20. ☒ Other items or information:

Int'l. Search Report; First Page of International Publication; IPEA Report; Certificate of Mailing;
Postcard;
PCT Appln. claims priority from Australian Patent Appln. Serial No. PP9225

U.S. APPLICATION NO. (if known, see 37 CFR 1.55)

09/936599

INTERNATIONAL APPLICATION NO.

PCT/AU00/00197

ATTORNEY'S DOCKET NUMBER

PHILLIPS-1

21. ☐ The following fees are submitted:**BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)):**

Neither international preliminary examination fee (37 CFR 1.482)
nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO
and International Search Report not prepared by the EPO or JPO. \$1000.00

International preliminary examination fee (37 CFR 1.482) not paid to
USPTO but International Search Report prepared by the EPO or JPO \$860.00

International preliminary examination fee (37 CFR 1.482) not paid to USPTO
but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$710.00

International preliminary examination fee (37 CFR 1.482) paid to USPTO
but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$690.00

International preliminary examination fee (37 CFR 1.482) paid to USPTO
and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00

ENTER APPROPRIATE BASIC FEE AMOUNT =**CALCULATIONS PTO USE ONLY**

\$ 1000.00

Surcharge of \$130.00 for furnishing the oath or declaration later than ☐ 20 ☒ 30
months from the earliest claimed priority date (37 CFR 1.492(e)).

\$ 130.00

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE	
Total claims	22 - 20 =	2	x \$18.00	\$ 36.00
Independent claims	3 - 3 =		x \$80.00	\$
MULTIPLE DEPENDENT CLAIM(S) (if applicable)			+ \$270.00	\$

TOTAL OF ABOVE CALCULATIONS =

\$ 1166.00

☒ Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above
are reduced by 1/2.

\$ 583.00

SUBTOTAL =

\$ 583.00

Processing fee of \$130.00 for furnishing the English translation later than ☐ 20 ☐ 30
months from the earliest claimed priority date (37 CFR 1.492(f)).

TOTAL NATIONAL FEE =

\$ 583.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be
accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +

TOTAL FEES ENCLOSED =

\$ 583.00

Amount to be
refunded:

charged: \$ 583.00

- a. ☐ A check in the amount of \$ _____ to cover the above fees is enclosed.
- b. ☒ Please charge my Deposit Account No. 04-1679 in the amount of \$ 583.00 to cover the above fees.
A duplicate copy of this sheet is enclosed.
- c. ☐ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any
overpayment to Deposit Account No. _____. A duplicate copy of this sheet is enclosed.
- d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. Credit card
information should not be included on this form. Provide credit card information and authorization on PTO-2038.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR
1.137 (a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

CRONK, Peter J., Esquire
Duane, Morris & Heckscher LLP
One Liberty Place
Philadelphia, Pennsylvania 19103-7396
United States of America

SIGNATURE

Peter J. Cronk, Esq.

NAME

Reg. No. 32,021

REGISTRATION NUMBER

PATENT

ATTORNEY DOCKET NO: Phillips-1

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of: Robert John Bolton and Kevin George Jarrett

Serial No.: not assigned

Examiner: not assigned


Filed: Herewith

Group Art Unit: not assigned

For: Radiation Curable Resin Composition

"Express Mail" Mailing Label No. EL714882137US

I hereby certify that this paper of fee is being deposited
with the United States Postal Service "Express Mail Post Office
To Addressee" service under 37 C.F.R. 1.10 on the date
indicated above and is addressed to the Assistant Commissioner
for Patents, Washington, DC 20231

September 14, 2001
DATE 

Assistant Commissioner for Patents
Washington, D.C. 20231

Dear Sir:

PRELIMINARY AMENDMENT

Prior to calculating the fee for the number of claims in this application, Applicants respectfully request that the following amendments be made:

In the Claims:

In claim 1, line 3, following "group consisting", please insert --essentially--.

In claim 14, line 1, please delete "any one of claims 6 to 9" and insert therefor --claim 6--.

In claim 20, line 1, please delete "any one of claims 17 to 19" and insert therefor
--claim 17--.

PATENT

ATTORNEY DOCKET NO: Phillips-1

Please insert the following abstract

--Abstract

Ultraviolet light curable resin compositions and methods of preparing radiation curable compositions are provided by this invention in which an amine adduct is formed by reaction of a secondary amine and epoxy and reacting the amine adduct with an unsaturated carboxylic acid to form a water soluble salt.--

REMARKS

The present application includes 22 claims, of which claims 1 and 17 are independent. The present preliminary amendment slightly broadens the preamble language of claim one to include minor chemical modifications to the claim formula which do not impact its properties. It also eliminates multiple dependency in claims 14 and 17. Since these claim amendments affect the calculation of fees relating to the claims, Applicants respectfully request that these amendments be entered prior to such calculation.


Dated: _____

9.14.01

DUANE, MORRIS & HECKSCHER LLP
One Liberty Place
Philadelphia, PA 19103-7396
tel 215-979-1252
fax 215- 979-1020

PHI\882770.1

Respectfully submitted,



Peter J. Cronk
Registration No. 32,021

Radiation Curable Resin Composition

09936599

The present invention relates to radiation curable resin compositions and to method of using such compositions.

5

The use of ultraviolet (UV) radiation or electron beam (EB) radiation as the energy source for cross linking functional monomers, oligomers and polymers is the basis of important commercial processes with broad applicability in photo imagery coatings inks and adhesive.

10

The most predominant type of resin systems used contain an oligomer such as epoxy acrylate, urethane acrylate or unsaturated polyester, a monomer diluent which is a polyunsaturated acrylic or vinyl monomer and an initiator.

- 15 The radiation curing processes, particular those involving UV radiation, generally rely on a polymerisation initiator which in the presence of the appropriate radiation generates activated species which initiate the polymerisation reactions and produce curing. Examples of photoinitiators used in UV curable composites include benzoin ethers such as benzyl methylether, hydroxydialkylacetophenones such as a α -hydroxy- α,α -dimethylacetophenone and 1-benzoylcyclohexanol, acylphosphine oxides, cyclic benzoin ethers, benzophenone, Michlers ketone and ketocoumarins.
- 20

The currently used radiation curable resin compositions are relatively expensive when compared with other coating systems due to the relatively high cost of resins, monomers and photoinitiators.

25

In many instances it is also difficult to achieve effective surface cure of the resins. Oxygen tends to inhibit polymerisation at the surface leading to undesirable surface tackiness. The use of certain photoinitiator combinations such as benzophenone and amines have been used to counteract this problem but may lead to undesirable odour or colouration. Inert gases have been used to reduce oxygen-inhibition but they are a further expense and are impractical in many commercial environments.

30

The existing compositions are also completely polymerisable to avoid the use of solvents or diluents. This makes it difficult in many instances to formulate semigloss and flat coatings or films of low film weight.

5

Furthermore many of the low viscosity, low molecular weight monomers have a high draize value and their use is minimized for health reasons.

10

We have now developed versatile radiation curable resin compositions which significantly reduces and in many cases eliminates the need for addition of a photoinitiator and which may address one or more further shortcomings of the prior art described above.

15

Accordingly we provide a radiation curable resin composition comprising a water soluble amine salt prepolymer formed between an oligomer having at least one amine group and an unsaturated carboxylic acid.

20

One of the significant advantages of the prepolymers used in the composition of the invention is their water solubility. The prepolymer may generally be diluted in water to at least 50% by weight permitting their use not only in high gloss but also matt or semi gloss films.

25

The weight ratio of the amine salt prepolymer to water in the resin composition of the invention is typically in the range of from 1:4 to 20:1 more preferably from 3:2 to 9:1 and most preferably from 3:2 to 8:1.

30

Despite their solubility in water the resins will generally polymerise on exposure to radiation after application to a substrate forming tough water resistant coatings without the need to take any special steps to remove water although drying may be promoted using known methods if desired.


The oligomer component of the salt may be selected from a range of oligomers. Typical example of suitable classes of oligomers include epoxy-amine adducts, amino resins such as urea formaldehyde and melamine formaldehyde type

resins, amine-polyisocyanate adducts, and Michael adducts of an aliphatic amine and polyacrylate or polymethacrylate compound.

- 5 The preferred oligomer components are selected from epoxy-amine and amino resins.


The most preferred prepolymers for use in the radiation curable composition of the invention are a salt of an epoxy-amine adduct and the unsaturated acid.

- 10 The epoxy resins from which the adduct may be formed are known in the art. One class of suitable epoxies is of the formula I:



n is from 0 to 10 and

- 15 A is a diradical selected from the group consisting of aliphatic, substituted aliphatic, aromatic, substituted aromatic, cycloaliphatic, substituted cycloaliphatic alkylene dicarbonyl and the diradical group of formula II:



- 20 wherein R is an alkylene group of 1 to 4 carbon atoms. Preferred group A include C₂ to C₂₂ alkyl dioxybenzene and C₄ to C₂₂ alkylene dicarbonyl and groups of formula II. Most preferably A is of formula II.

- 25 The most preferred epoxy is a condensation product of bisphenol A and epichlorohydrin.

- The amine will generally react with the terminal epoxy groups to form one or more terminal amine groups depending on the stoichiometry of the reaction. In cases where the stoichiometry used does not produce a reaction with all epoxy groups the remaining groups may be reacted to provide other functional groups
- 30

such as ester groups by reaction with unsaturated acids or ethers by reaction with alcohols or alcohol groups by reaction with water.

5 The stoichiometry of the epoxy amine adduct is preferably in the range of from 0.5 to 2.05 mole of amine compound per mole of epoxy compound, more preferably from 0.95 to 1.6 and most preferably from 1.0 to 1.5.

10 The reaction between the epoxy and amine is exothermic and if allowed to proceed may produce an undesirably viscous resin. It is therefore preferable to control the reaction temperature and also quench the reaction by combining the reaction product with water and preferably stirring the aqueous mixture. The unsaturated acid is preferably added to the aqueous mixture and generally produces a clear resin solution. In this case excess unreacted epoxy groups may react with water to form diols.

15 A further embodiment of the invention uses amino resins. The preferred amino resins are based on the reaction products of formaldehyde and urea or melamine. Formaldehyde reacts with urea to form resins which are generally bifunctional. Melamine on the other hand reacts with formaldehyde to form
20 trifunctional resins.

Urea and melamine with formaldehyde and glyoxal are the basic materials but melamine may be partly or completely replaced by benzoguanamine and acetoguanamine. Urea/formaldehyde and/or melamine/formaldehyde are the
25 preferred amino resins. Further examples of preferred type of amino resins include ethylene urea, a resin based on dimethylolethylene urea is prepared from urea, ethylene diamine and formaldehyde; propylene urea-formaldehyde, a resin prepared from urea, 1,3-diamino-propane and formaldehyde; triazone resin made from urea, formaldehyde and a primary aliphatic amine such as
30 hydroxyethylamine; uron resins, mixtures of a minor amount of melamine resin and uron (predominantly N,N'-bismethoxymethyl) uron plus about 25% methylated urea formaldehyde; glyoxal resin prepared from urea and/or melamine, glyoxal and formaldehyde and one or more alcohols such as ROH where R is alkyl or an alkyl hydroxy alkyl or alkyl ether of ethylene glycol;

melamine-formaldehyde which include the dimethyl ether of trimethylolmelamine; and methylol carbamate resins, derivatives made from urea and an alcohol, ROH wherein R is an alkyl, hydroxy alkyl or alkyl ether of ethylenglycol.

5

The more preferred amino resins include melamine and formaldehyde and optionally glyoxal and/or urea.

10 The preferred melamine formaldehyde resins are of the glyoxal type and are prepared from melamine, formaldehyde, glyoxal and preferably further including one or more alcohols selected from the group consisting of C₁ to C₆ alkanols, C₁ to C₆ alkyl ethers of C₁ to C₆ alkylene glycols and C₁ to C₆ alkylene glycols. To provide good shelf stability it is particularly preferred to include an alcohol. We have also found the efficiency of cure of melamine formaldehyde resins may be
15 improved in many cases by using an acid buffering agent such as phosphoric acid to preferably provide a pH of less than 5.

20 The oligomer compound of the composition of the invention may be a urethane amine adduct. The amine adduct may be prepared by reaction of an amine with a polyisocyanate. The polyisocyanate may be a simple polyisocyanate such as toluene diisocyanate, diphenylmethane-4,4-diisocyanate or hexamethylene diisocyanate or may be prepared by reaction of a polyol and polyisocyanate. Examples of suitable polyol components include polyester polyols, polyether polyols and polyester polyether block copolymers.

25

The molar ratio of amine to polyisocyanate used in forming the adduct is typically from 0.90 to 1.6 and most preferably from 1 to 1.5.


30 Urea groups may be prepared from isocyanate groups of a urethane prepolymer by reaction with water. The preferred urethane amine adduct is based on an aromatic isocyanate.

The oligomer component of the composition of the invention may be a michael adduct formed by reactions of amine with a multifunctional acrylate or

methacrylate monomer or prepolymer or mixture of two or more thereof. The michael adduct is preferably formed between a secondary amine and an unsaturated carboxylic acid selected from monomers and oligomers containing a plurality of unsaturated groups including at least one acrylate or methacrylate group. Examples of suitable multifunctional acrylates and methacrylates include urethane acrylates, urethane methacrylates, diisocyanates, polyol diacrylates and dimethacrylates, alkylene diacrylates, alkylene dimethacrylates, oligoester diacrylates and oligoester dimethacrylates wherein the oligoester portion may be formed by reaction of adipic, phthalic, isophthalic acid or their anhydrides with polyols such as alkylene glycol or polyalkylene glycol as well as triols such as trimethylol propane and tetrols such as pentaerythritol.


Examples of michael adducts are described in US Patent 3844916 (Gaske) and will preferably be formed by reaction of a secondary amine and multifunctional acrylate/methacrylate.

The Michael adducts will generally include an amino group of formula III as a result of the addition:



wherein R and R¹ are preferably as defined below for the amine of formula IV and R² is methyl or hydrogen.


The amine group or groups which are present in the prepolymer component of the composition of the invention are preferably selected from secondary amines, secondary alkanolamines and mixtures of two or more compounds from these groups. The preferred amines are of formula IV:



wherein R and R¹ are independently selected from the group consisting of straight and branched chain aliphatic of up to 10 carbon atoms optionally substituted by hydroxy and preferably R and R¹ are C₁ to C₆ alkyl optionally substituted by hydroxy. The hydroxy substitution is preferably on a primary carbon atom which is not directly adjacent an amino nitrogen. Particularly preferred R and R¹ are ethyl, 2-hydroxy ethyl, propyl, 3-hydroxypropyl. Most preferably the amine is diethylamine or diethanolamine.

It is preferred that the amine component is substantially free of primary amine and preferably it contains less than 5% by weight of primary amine. This is particularly preferred where the oligomer is an amine adduct of an epoxy or polyisocyanate. The presence of amine compositions containing at least 95% secondary amine and preferably at least 98% produces lower viscosity resins which tend to have better long term stability.

The oligomer component of the radiation curable resin composition of the invention is in the form of a salt with an unsaturated carboxylic acid. The preferred unsaturated acids are αβ unsaturated carboxylic acid particularly those selected from the group consisting of acrylic acid, citraconic acid, sorbic acid, fumaric acid and mixtures of two or more thereof. The preferred unsaturated acids are compounds of the formula:



wherein R is hydrogen C₁ to C₄ alkyl and preferably hydrogen or methyl. The preferred unsaturated acids are thus acrylic acid and methacrylic acid. Mixtures of two or more unsaturated acids may also be used.

The molecular weight of the oligomer resins used in the composition of the invention may vary significantly depending on their proposed use and concentration. Typically the molecular weight of the oligomer salt is in the

range of from 500 to 20,000 more preferably from 700 to 10,000 and most preferably from 1000 to 3000.

5 The resins compositions of the invention may be used in aqueous formulations to form coatings by UV radiation curing. No added initiators are generally required to obtain efficient UV curing although they may be used if desired. Typically the composition will contain less than 0.5% by weight of added initiators and are most preferably free of added photoinitiators. Polymerisation under UV occurs rapidly without generally needing to dry the water used in forming the salts. The UV cured film forms a tack free surface at the air interface.

15 The composition of the invention is preferably a coating composition or an ink. The composition may be formulated with suitable additives. Examples of suitable additives include surfactants, antifoam agents, inhibitors, pigments, fillers and other resins. Solvents may be included if desired yet are generally not required.

20 Surfactants may be used where the composition is to be used as a coating for greasy surfaces such as for overcoating inks. Examples of suitable surfactants include silicone derivatives, vinyl silanes and fluorinated wetting agents such as fluoroalkyl ethers.

25 Inhibitors may be used to inhibit gelling of the composition during storage. Examples of inhibitors include hindered amines such as diphenylamine, phenothiazine and di-p-fluorophenylamine; phenolic and quinone/hydroquinone compounds such as hydroquinone, mono-tertbutylhydroquinone, benzoquinone, 2,5-diphenyl-p-benzoquinone, p-methoxyphenol and 2,6-di-tert-butyl-cresol. Inhibitors are generally used in amount of from 0.01 to 1% and preferably 0.01 to 0.5% by weight.

In a further aspect the invention provides a method of preparing a radiation curable composition comprising forming an amine adduct by reacting of a

secondary amine with an epoxy and reacting the amine adduct with an unsaturated carboxylic acid to form a water soluble salt.

5 The amine adduct and unsaturated carboxylic acid are generally reacted in the presence of water. The reaction which takes place between a secondary amine and epoxy or polyisocyanate is exothermic and we have found that particularly good results are obtained if the reaction mixture of the epoxy or polyisocyanate and secondary amine are diluted with water during the exotherm. This may be done by adding an excess of water or by pouring the reaction mixture into
10 water.

It is surprising to find that the compositions of the invention are generally polymersable by standard UV radiation equipment without the need to use a photoinitiator. The most preferred resins from this point of view are the
15 unsaturated acid salts of epoxy-amine adducts and amine resins. Isocyanate adducts are in some cases less sensitive and may require addition of small amount of for example up to 0.5% by weight of photoinitiator. The reduction or elimination of the photoinitiator component significantly reduces the cost of compositions of the invention when compared with traditional UV curable
20 coatings. Furthermore the component used in preparing the compositions of the invention may be chosen from inexpensive resins, the components of which are readily available. The relatively expensive monomer components required in many prior art compositions can be avoided.

25 The sensitivity of the compositions of the invention can be compared for different resins and with prior art compositions using the following curing test.

In the curing test a coating film of 5 microns is drawn down on a substrate and is exposed to ultraviolet light of 25 millijoules per cm². The amount of energy
30 may be measured using a suitable radiometer such as an EIT Uvicure Radiometer Model M365. The lamp which we used in our test was a mercury lamp of 80 w/cm at half power (40 w/cm) and we used a belt speed of 35 metres per minute.

The compositions of the invention will generally cure under the above test conditions with addition of less than 0.5% based on resin component of initiator and the compositions of the invention will in most cases require no added photoinitiator. In contrast compositions of the prior art generally require 5% photoinitiator based on the resin component.

Although the resin compositions generally cure without addition of a photoinitiator the compositions may, if desired contain conventional initiators. Typically when used the photoinitiator will be present in an amount of less than 0.5% by weight based on the total weight of the resin component.

The resin composition is typically prepared as an aqueous solution containing at least 10% by weight oligomer salt. The aqueous solution will typically contain in the range of from 20 to 95% by weight of the resin salt preferably from 50 to 85% and most preferably in the range of from 60 to 80% by weight of resin.

A further significant advantage of compositions of the invention is that their cure is generally not significantly inhibited by oxygen when cured in air. As previously indicated the curing of conventional compositions are inhibited by oxygen in air making it difficult to rely on UV curing for preparing coatings without excluding air by using an inert gas or specific initiator combinations which further increase costs.

The ability to prepare the resins at a range of concentrations makes them particularly versatile in controlling gloss levels. Flat films may be prepared using a relatively dilute composition such as from 40 to 65% by weight resin in water. Gloss films on the other hand may contain 65 to 90% by weight resin in water.

Prior art compositions made it difficult to achieve the same properties without the compositions being undesirably viscous or containing a high proportion of relatively expensive monomer diluent.

Even though the compositions of the invention are prepared and used as an aqueous solution they dry to form a water resistant film which is durable and resistant to solvents.

- 5 The compositions of the invention are also relatively non hazardous to skin contact and are essentially odour-free.

Each of these advantages alone has merit and collectively the advantages of compositions of the invention constitute a major commercially attractive
10 advance to the field of radiation cured coatings.

The invention will now be described with reference to the following examples. It is to be understood that the examples are provided by way of illustration of the invention and that they are in no way limiting to the scope of the invention.

15

Examples 1 to 7

These examples demonstrates preparation of compositions of the invention in which a portion of the epoxy groups are pre-reacted with acrylic acid prior to addition of a secondary amine to form the epoxy amine adduct and
20 subsequently formation of the amine/acrylic acid salt.

To 0.1 mole (36gm of bisphenol A diglycidyl ether (Araldite 6010) is added varying amounts of acrylic acid together with 0.1g hydroquinone monomethyl ether inhibitor and 0.5g catalyst. The mixtures are reacted at 100°C for 40
25 minutes and then cooled to 95°C, and diethanolamine is added over several minutes, allowing the subsequent exotherm to proceed to 140-150°C with no external heat. The product is allowed to cool to 90°C, and water is then added with rapid stirring producing a white stable dispersion. Acrylic acid is then added slowly with continuous stirring to solublise the resin solution.

30

After 15 minutes, the solution is allowed to cool, inhibitor added and transferred to a dark glass container.

1	36g (0.1 mol)	5.8g (0.08 mole)	12.6g (0.12 mol)	20g	10g	>1p
2	36g (0.1 mol)	5.6g (0.09 mol)	11.5g (0.11mol)	20g	7g	>1p
3	36g (0.1 mol)	7.2g (0.10 mol)	10.5g (0.10 mol)	20g	6g	420cp
4	36g (0.1 mol)	7.9g (0.11 mol)	9.5g (0.09 mol)	20g	6g	980cp
5	36g (0.1 mol)	8.6g (0.12 mol)	8.4g (0.08 mol)	20g	5g	110cp
6	36g (0.1 mol)	9.4g (0.13 mol)	7.4g (0.07 mol)	20g	6g	620cp
7	36g (0.1 mol)	10.1g (0.14 mol)	6.3g (0.06 mol)	20g	4g	>1p

Each sample was then coated onto calendared paper at 5 microns using a wire wound applicator, and passed under UV light at 15m/minute. Each film was examined for gloss, surface tack, hardness, water and MEK resistance. The results were as follows:

Examples 3, 4 and 5 all cured after one pass to give satisfactory films.

Examples 1 and 2 were more difficult to apply due their viscosity and required two passes to cure.

Examples 6 and 7 were slightly more turbid and produced dull films.

Example 8

This example and examples 9 to 21 below demonstrate the preparation of an epoxy amine resin which is reacted with an unsaturated acid to form a resin salt in accordance with the invention. One mole of bisphenol A diepoxide resin was reacted with at least 1 mole of diethanolamine to form an adduct. Allowing the exotherm of this reaction to take its course over 5-10 minutes. The composition was diluted with water or quenched into water to form a stable dispersion of the adduct. To this dispersion, 2 moles of acrylic acid or methacrylic acid were added to produce a cationic resin solution, with very similar properties of those resins formed from epoxy acrylate half ester described in Examples 1 to 7. These resins have low odour and colour and will photopolymerise, when exposed to UV light, to a hard tack-free state.

The resin is of low viscosity and permits solids contents of at least 80%, with as little as 20% water, and have moderately low viscosity. The overall reaction

time can be accomplished within 1 hour, by avoiding the longer ester formulation of the method described in Examples 1 to 7. The resins of this example appears to show reduced tendency to auto-polymerise.

5 Example 9

Bisphenol di-glycidyl ether resin (1 mole) 360g is mixed with diethanolamine (1 mole) 105g at room temperature, and heated with stirring to 70°C, when it forms a clear homogeneous mixture. At this stage an energetic reaction takes place and the external heat is removed. The resultant exotherm increases the temperature rapidly to 140-150°C with a corresponding reduction in viscosity of the clear fluid. This is rapidly poured into (10 moles) 180g of cold water, with fast stirring to produce a white dispersion, with corresponding increase in temperature of the resin mixture. Acrylic acid (2 moles) 144g, is added over several minutes and a clear resin solution results. The resin solution is allowed to cool, with continuous stirring. The resultant resin is a clear, colourless, low viscosity oligomer solution with almost no odour and a pH of 4-6. When cast as a thin film onto a metal or paper substrate, and exposed to UV light for a few seconds, the resin rapidly produces a hard, tack-free and odour-free clear glossy film, with good water and solvent resistance.

20

Examples 10-15

The procedure of Example 8 was followed with the exception that water was added to the resin at the stage of exotherm in which the resultant reflux of water assisted in controlling the heat and provided the dispersion prior to salt formation. Different amines and unsaturated acids were also examined.

25

Example	E10	E11	E12	E13	E14	E15
	Moles	Moles	Moles	Moles	Moles	Moles
BPDGE (Araldite 6010)	1.0	1.0	1.0	1.0	1.0	1.0
Diethanolamine	1.0	1.0	1.3	1.6	1.0	1.0
Water	10.0	10.0	10.0	10.0	10.0	10.0
Acrylic acid	1.0	2.0	2.0	2.0	-	-
Methacrylic acid	-	-	-	-	1.0	2.0

Each of these resin solutions was a clear low viscosity solution and produced a hard glossy film after exposure to UV radiation. Example 13 did show a tendency to water sensitivity at the higher ratio of diethanolamine.

5 Examples 16-21

	216	217	218	219	220	221
	Moles	Moles	Moles	Moles	Moles	Moles
BPDGE (Araldite 6010)	1.0	1.0	1.0	1.0	1.0	1.0
Diethanolamine	1.0	1.0	1.3	1.6	1.0	1.0
Diethylamine	-	1.0	0.7	0.4	-	-
Urea	-	-	-	-	0.5	1.0
Water	10	10	10	10	10	10
Acrylic acid	2.0	2.0	2.0	2.0	2.0	2.0

These resins displayed differences in viscosity, but each was photocurable and produced satisfactory films.

10

Examples 22-28

These examples examine preparation of compositions of this invention using melamine formaldehyde based resins.

15 Example 22

To 324g of 37% formalin (4 moles) is added 126g of melamine (1 mole) at room temperature and heated with stirring, to 70°C and held until clear, about 40 minutes. The solution is cooled to 45°C and 145g of 40% glyoxal (1 mole) is added with constant stirring, and held for a further 30 minutes. A clear pale
 20 amber solution results, to which is added 144g of acrylic acid (2 moles), and allowed to cool. The resultant solution is a very pale, clear and odour-free solution which when cast onto a metal or paper substrate and exposed to UV radiation, will cure rapidly to a hard, tack-free and odour-free clear film, with good water and solvent resistance.

25

The procedure of Example 22 was repeated using various proportions of components and alcohols as shown in the table below.

	Moles	Moles	Moles	Moles	Moles	Moles
Formalin 37%	3	3	3	3	3	3
Glyoxan 40%	1	1	1	1	1	1
Melamine	1	1	1	1	1	1
Ethanol	-	2	-	-	2	-
n-Propanol	-	-	2	-	-	2
Hydroxy ethyl acrylate	-	-	-	1	-	-
Acrylic acid	2	2	2	-	1	2

5

Example 29

In a similar manner, to 324g of 37% formalin (4 moles) is added 126g of melamine and also 240g of n-propanol (4 moles) and heated with stirring to 65°C and held for 30 minutes. A clear solution results which smells faintly only of propanol, to which is added 144g of acrylic acid (2 moles), and the stirring continued for a further 30 minutes at 50°C, then cooled. This resin solution behaves in the same way as Example 12, will UV cure to a clear glossy film with faint odour of propanol. It does appear to be slightly more flexible in thicker films than Example 22 films.

15

Example 30-33

Resins were prepared according to Example 29 but replacing n-propanol with methanol (Example 30), ethanol (Example 31), butanol (Example 32) and isopropanol (Example 33). Each resin responded to UV radiation. The isopropanol resin was the least reactive thought to be due to steric hindrance. The resin based on n-butanol had a stronger residual odour.

20

Example 34

Other resins were made from monofunctional epoxides, by similar reactions to that described in Example 1 to 7 except that the full diethanolamine adduct was

25

formed, followed by salt formation with acrylic acid. Six typical examples were made from cresol glycidyl ether, butanediol glycidyl ether, C12-14 alkyl glycidyl ether, neodecanoic acid diglycidyl ester, as well as butanediol di glycidyl ether and an alicyclic diepoxy carboxylate. These all exhibited some of the desired properties as indicated above, yet were all of lower viscosity and less water resistant.

Example 35

To 65g(0.8 moles)of 37%formalin was added 24.5g urea(0.4 moles)and 48g n-propanol (0.8 moles)and heated with stirring to 60 degrees C, and held for 20 minutes. Heat was stopped and acrylic acid 60g (0.8 moles)slowly added over 3 minutes with continuous stirring. At about 40 degrees, phosphoric acid 1 g was added and then cooled to room temperature. The resulting clear liquid resin was found to UV cure to a soft film which continued harden on further irradiation.

Similarly, resins were prepared by replacing propanol with 36g of ethanol which gave a clear resin product with similar properties.

Example 36

To 33g (0.4 moles) 37%formalin was added 16g (0.13 moles) melamine and 2.0 g diethanolamine heated with stirring to 60 degrees C and held for 10 minutes,16g (0.25 moles) n-propanol was added and held at 60 degrees for a further 20 minutes. The resin was cooled to 30 degrees and acrylic acid 18g (0.25 moles)and phosphoric acid 2g added and stirred until cold. The resultant clear resin cures to a dry glossy film under UV radiation.

A similar batch was prepared except acrylic acid was increased by 50% to 27g (0.38 moles) and no phosphoric acid. This resin was very similar and UV cured as before.

A third resin was prepared by replacing propanol with 14 g (0.25 moles) of ethanol and then adding 18 g acrylic acid and 2g phosphoric acid. This resin behaved as in the other cases.

5 **Example 37**

Using the same general procedure urea (1 mole, 60g) was reacted with Glyoxal (1 mole, 145g of a 40% solution) and then acrylic acid (2 moles, 144g) added to form a salt. The resultant solution was capable of UV cure but the so formed film was water sensitive.

10

Example 38

One mole of propylene oxide (58g) was carefully added to one mole (105g) of diethanolamine, and allowed to cool. Water (20g) was added and then one mole (72g) of acrylic acid. The adduct was tested as before and found to be water soluble, low odour and colour, low viscosity but only partially cures under UV radiation.

15

Example 39

This example demonstrates preparation of compositions of the invention from michael adducts. One mole of tri propylene glycol diacrylate (300g) was mixed with one mole (105g) of diethanolamine and heated to 105°C and held for 30 minutes. The product was then cooled to 90°C and 90g water added with stirring. 1 mole (72g) of acrylic acid was slowly added. On testing for cure, this resin was found to cure only with 1-2% of photoinitiator (Irgacure 184).

20

25

Example 40

To the resin of Example 3 was added 20% of aqueous pigment dispersions based on carbon black, diarylide yellow and phthalocyanine blue were added with stirring. These pigmented compositions were stable and when cast out as films and exposed to UV radiation, cured in a similar manner to the unpigmented resins previously described. The presence of pigment adversely affects the rate of cure, and small additions of photoinitiator may be used to accelerate the cure.

30

Example 41 and Comparative Example A

The composition of Example 20 was formed into a coating composition for use as a high gloss overprint varnish having the following compositions

5

Example 41

Component	Parts by Weight
Epoxy acrylate (Ex 20)	80.0
PA57 silicone glycol copolymer levelling agent	0.5
"Quatramine C16/50" (50% active solution of trimethyl hexadecyl ammonium chloride in a mixture of water and ethanol (levelling agent))	4.5
Water	15.0
	100.0

Viscosity Brookfield RVT #4/100/25°C = 460 cps.

10

The composition was drawn down to a 5 micron coating on printed paper stock and cured using a mercury UV lamp of 80 w/cm at half power (ie 40 w/cm) half speed of 35 meters per min to provide a UV lamp energy of 25 millijoules per cm². The radiometer used to measure energy was a EIT Uvicure Radiometer model M365. The composition of the invention cured without addition of photoinitiator.

15

A conventional UV curable high gloss overprint varnish was prepared with the following composition.

20

25

Comparative Example A

Component	Parts by Weight
Craynor CN104 A80 = Epoxy Acrylate cut with 20% T.P.G.D.A.	43.0
T.M.P.E.O.T.A. = Ethoxylated Trimethylolpropane Triacrylate	48.5
Methyldiethanolamine = Amine synergist	3.0
Benzophenone, Photoinitiator	3.0
Irgacure 184 = 1-Hydroxy-cyclohexyl-phenyl-ketone, Photoinitiator	2.0
PA57 = Silicone glycol Copolymer (levelling and slip agent)	0.5
	100.0

Viscosity = Brookfield RVT #4/100/25°C = 460 cps

5


The prior art composition required 5% photoinitiator and 3% amine synergist to cure under the same conditions.

10


Those skilled in the art will appreciate that there may be many variations and modifications of the configuration described herein which are within the scope of the present invention.

Claims:

1. An ultraviolet light curable resin composition comprising a water soluble amine salt prepolymer formed between an unsaturated carboxylic acid and an oligomer having at least one amine group selected from the group consisting essentially of urea formaldehyde resins, melamine formaldehyde resins, amine polyisocyanate adducts, Michael adducts of a secondary amine and acrylate and/or methacrylate compounds and epoxy-amine adducts formed between an amine and epoxy of formula:



wherein n is from 0 to 10 and A comprises a diradical selected from the group consisting of aromatic, substituted aromatic and the diradical of formula II:




wherein R is an alkylene group of 1 to 4 carbon atoms.

2. A resin composition according to claim 1 comprising an aqueous solution containing a weight ratio of amine salt prepolymer to water in the range of from 1:4 to 20:1.
3. A resin composition according to claim 2 wherein said weight ratio is in the range of from 3:2 to 9:1.
4. A resin composition according to claim 1 which is curable by UV and contains less than 0.5% by weight based on the weight of the resin component of a UV initiator.


21

5. A resin composition according to claim 1 which is curable by UV in the absence of photoinitiator.

6. A resin composition according to claim 1 wherein the oligomer having at least one amine group is an epoxy-amine formed between a secondary amine and an epoxide of formula 1:



wherein n is from 0 to 10 and A is a diradical of formula II:



wherein R is an alkylene group of 1 to 4 carbon atoms.

7. A resin composition according to claim 6 wherein the epoxide of formula 1 is a product of epichlorohydrin and bisphenol A.

8. A resin composition according to claim 6, wherein the amine adduct is formed using a molar ratio of amine to epoxide compound in the range of from 0.5:1 to 2.05:1.


9. A resin composition according to claim 6 wherein the molar ratio of amine to epoxide compound is 0.95:1 to 1.6:1.

10. A resin composition according to claim 1 wherein the oligomer having at least one amine group is prepared from melamine, formaldehyde and/or glyoxal and optionally one or more alcohols selected from the group consisting of C₁ to C₆ alkanols, C₁ to C₆ alkyl ethers of C₁ to C₆ alkylene glycols and C₁ to C₆ alkylene glycols.

AMENDED SHEET
IPEA/AJ

W:\chem\spec\spec200187 W\Odn2 1May01.doc

11. A resin composition according to claim 1 wherein the oligomer having at least one amine group is a urethane-amine adduct prepared by reaction of a secondary amine with a polyisocyanate.
12. A resin composition according to claim 1 wherein the urethane amine adduct is formed from a molar ratio of amine to polyisocyanate of from 0.90:1 to 1.6:1.
13. A resin composition according to claim 1 wherein the oligomer having at least one amine group is a Michael adduct formed between a secondary amine and an unsaturated compound selected from the group consisting of monomers and prepolymers comprising a plurality of unsaturated groups including at least one acrylate or methacrylate group.
14. A resin composition according to claim 6 wherein the secondary amine is amine of formula IV:



- wherein R and R¹ are independently selected from straight and branched chain aliphatic of up to 6 carbon atoms optionally substituted by hydroxy and mixtures thereof.
15. A resin composition according to claim 1 wherein the unsaturated acid is selected from the group consisting of acrylic acid, methacrylic acid, crotonic acid, citraconic acid, sorbic acid, fumaric acid and mixtures of two or more thereof.
16. A resin according to claim 1 wherein the unsaturated acid is selected from the group consisting of acrylic acid and methacrylic acid.
17. A method of preparing a radiation curable composition comprising forming an amine adduct by reaction of a secondary amine and an epoxy and

23

reacting the amine adduct with an unsaturated carboxylic acid to form a water soluble salt.

18. A method according to claim 17 wherein the amine adduct and
5 unsaturated carboxylic acid are reacted in the presence of water to provide an aqueous solution of a salt formed between the epoxy amine adduct and unsaturated carboxylic acid.

19. A method according to claim 17 wherein the reaction of the secondary
10 amine and epoxy is exothermic and the reaction mixture is diluted with water during the exotherm.

20. A method according to claim 17 wherein water is
added to provide a concentration of from 20 to 95%.

21. A method of forming a coating on a substrate comprising applying to the
15 substrate a layer of an aqueous solution of a radiation curable resin according to claim 1 and subjecting the layer of said aqueous solution to ultraviolet radiation to cure the layer.

22. The method according to claim 21 wherein the composition is applied at
20 a thickness of up to 200 microns.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08G 12/40, 18/83, 59/17, C08F 2/44, 8/44, 283/00, C09D 4/06, 133/02, 133/14, 151/08, 161/32, 163/10		A1	(11) International Publication Number: WO 00/55228 (43) International Publication Date: 21 September 2000 (21.09.00)
(21) International Application Number: PCT/AU00/00197 (22) International Filing Date: 17 March 2000 (17.03.00) (30) Priority Data: PP 9225 17 March 1999 (17.03.99) AU (71)(72) Applicants and Inventors: BOLTON, Robert, John [AU/AU]; 6 Coventry Place, West Pymble, NSW 2073 (AU). JARRETT, Kevin, George [AU/AU]; 3B Niland Way, Casula, NSW 2170 (AU). (74) Agent: PHILLIPS ORMONDE & FITZPATRICK; 367 Collins Street, Melbourne, VIC 3000 (AU).		(81) Designated States: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	
(54) Title: RADIATION CURABLE RESIN COMPOSITION (57) Abstract A radiation curable resin composition comprising a water soluble amine salt prepolymer formed between an oligomer or compound having at least one amine group and an unsaturated carboxylic acid and use of this composition as a surface coating or ink.			

2042440 6653550

COMBINED DECLARATION AND POWER OF ATTORNEY

As a below-named inventor, I hereby declare that:

My residence, post office address, and citizenship are as stated below next to my name; and

I verily believe that I am the original, first and sole inventor (if only one name is listed below) or an original, first, and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention **RADIATION CURABLE RESIN COMPOSITION** the specification of which:

☒ [X] is attached hereto.

☐ [] was filed on _____ as Application Serial No. _____ and was amended on _____. (If applicable.)

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any Amendment referred to above.

I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with 37 C.F.R. §1.56.

I hereby claim foreign priority benefits under 35 U.S.C. §119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of any application on which priority is claimed:

Country	Number	Date Filed	Priority Claimed?
<u>AU</u>	<u>PP9225</u>	<u>03/17/1999</u>	<u>Yes</u>
_____	_____	_____	_____
_____	_____	_____	_____
_____	_____	_____	_____

I hereby claim the benefit under 35 U.S.C. § 119(e) of any United States Provisional Application listed below:

ATTORNEY DOCKET: PHILLIPS-1

PATENT

Application	Filed	Patented or
Serial No.		Pending?

I hereby claim the benefit under 35 U.S.C. §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of 35 U.S.C. §112, I acknowledge the duty to disclose material information as defined in 37 C.F.R. §1.56(a) which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

Application	Filed	Patented or
Serial No.		Pending ?

I hereby appoint the following attorneys, of the law firm **DUANE, MORRIS & HECKSCHER LLP**, One Liberty Place, Philadelphia, PA 19103-7396, to prosecute this application and to transact all business in the United States Patent and Trademark Office connected therewith,

Attorney Name(s):

- Arthur L. Plevy (Reg. No. 24,277)
- Lewis F. Gould, Jr. (Reg. No. 25,057)
- William H. Murray (Reg. No. 27,218)
- Stephan P. Gribok (Reg. No. 29,643)
- Peter J. Cronk (Reg. No. 32,021)
- Richard Redano (Reg. No. 32,292)
- Robert E. Rosenthal (Reg. No. 33,450)
- Richard A. Paikoff (Reg. No. 34,892)
- Jane E. Alexander (Reg. No. 36,014)
- Samuel W. Apicelli (Reg. No. 36,427)
- Steven E. Koffs (Reg. No. 37,163)
- Paul A. Schwarz (Reg. No. 37,577)
- Darius C. Gambino (Reg. No. 41,472)
- Carl A. Giordano (Reg. No. 41,780)
- Anthony Colesanti (Reg. No. 42,428)
- Edward J. Howard (Reg. No. 42,670)
- Gary Maze (Reg. No. 42,851)
- Richard Wong (Reg. No. 45,572)
- Melanie Goddard (Reg. No. 46,732)
- Joseph Powers (Reg. No. 47,006)
- Joseph F. Oriti (Reg. No. 47,835)

(21)

ATTORNEY DOCKET: PHILLIPS-1

PATENT

and

Address all correspondence to:

Peter J. Cronk, Esquire.
DUANE, MORRIS & HECKSCHER LLP
One Liberty Place
Philadelphia, PA 19103-7396

Please direct all telephone calls to Peter J. Cronk at (215) 979-1252.

I hereby declare that all statements made herein of my own knowledge are true, and that all statements made on information and belief are believed to be true, and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. §1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

04240 65932660

1	Full Name Robert John Bolton	Inventor's Signature <i>Robert John Bolton</i>	Date 11/4/02
	Residence 6 Coventry Place West Pymble New South Wales 2073 AUSTRALIA Citizenship: Australia <i>AUX</i> Post Office Address same as above <i>YES</i>		
2	Full Name Kevin George Jarrett	Inventor's Signature <i>Kevin George Jarrett</i>	Date 11/4/02
	Residence 3B Niland Way Casula New South Wales 2170 AUSTRALIA Citizenship: Australia <i>AUX</i> Post Office Address same as above <i>YES.</i>		
3	Full Name	Inventor's Signature	Date
	Residence Citizenship: Post Office Address		
4	Full Name	Inventor's Signature	Date
	Residence Citizenship: Post Office Address		

207270 65533660